Dam:	3 de Febrero (formerly El Chaparral)	Country	El Salvador
River	Torola	13°51'46.94"N 88°21'3"W	13.863039 -88.35083
Owner/Client	Comisión Ejecutiva Hidroeléctrica del Rio Lempa (CEL)		
Designer/Engineer	Intertechne Consultores Associados		
Contractor	Astaldi (contract terminated) and UDP/Cartellone (Argentina)/Holcim JV		

Purpose (code)	H
Site start	01.01.2009
RCC start	01.01.2018
RCC completion	31.12.2020
Site completion	19.10.2023
Height (m)	88
Length (m)	324
Volume of RCC (m^3x10^3)	375
Total volume (m^3x10^3)	450
Reservoir capacity (m^3x10^6)	*Unknown*
Upstream slope	0.20
Forming of upstream face (code)	(7')
Downstream slope	0.80
Forming of downstream face (code)	(7')
Spillway slope	0.80
Forming of spillway face (code)	(7')
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	94
Pozzolan content (kg/m^3)	63
Code for pozzolan	(N)
RCCDAM Unique Serial No.	RCCDAM0691

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines