

Dam: Dahuashui

Country: China

River: Qingshuihe

26°48'54.49"N 107°15'45.03"E

26.815136 107.262505

Owner/Client: Wujaing Qingshuihe Hydropower Development Co. Ltd.

Designer/Engineer: Guiyang Hydroelectric Investigation, Design and Research Institute, CHECC

Contractor: 8th and 9th Construction Bureaux

Purpose (code): F H

Site start: 01.12.2003

RCC start: 01.04.2005

RCC completion: 30.11.2006

Site completion: 31.12.2007

Height (m): 135

Length (m): 198

Volume of RCC (m³x10³): 550

Total volume (m³x10³): 670

Reservoir capacity (m³x10⁶): 276

Upstream slope: curve

Forming of upstream face (code): (3')

Downstream slope: curve

Forming of downstream face (code): (3')

Spillway slope: Unknown

Forming of spillway face (code): (1)

Depth of layers (mm): 300

Depth of lifts (mm): 3000

Cement content (kg/m³): 81
94

Pozzolan content (kg/m³): 81
94

Code for pozzolan: (F)

RCCDAM Unique Serial No.: RCCDAM0361

Completed Dam



RCCDAM0361CD

Google Earth



RCCDAM0361GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines