

Dam: Gassan

Country Japan

River Bonji

38°34'58.99"N 139°53'43.09"E

38.583054 139.895309

Owner/Client Ministry of Construction

Designer/Engineer Ministry of Construction

Contractor Nishimatsu Construction Co Ltd, Obayashi-Gumi Co Ltd and Tekken Construction Co Ltd J.V.

Purpose (code) F H I W

Site start 23.08.1988

RCC start 16.06.1994

RCC completion 05.10.1998

Site completion 21.03.2001

Height (m) 123

Length (m) 393

Volume of RCC ($m^3 \times 10^3$) 731

Total volume ($m^3 \times 10^3$) 1160

Reservoir capacity ($m^3 \times 10^6$) 65

Upstream slope V

Forming of upstream face (code) (1)

Downstream slope 0.80

Forming of downstream face (code) (1)

Spillway slope 0.80

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm)
750
1000

Cement content (kg/m^3) 91

Pozzolan content (kg/m^3) 39

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0200

Completed Dam



RCCDAM0200CD

Google Earth



RCCDAM0200GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines