

Dam: Hinata

Country Japan

River Kasshi

39°17'35.55"N 141°47'52.74"E

39.293209 141.797989

Owner/Client Iwate Prefecture

Designer/Engineer Iwate-ken

Contractor Hazama-gumi Co Ltd and Chizaki Kogyo Co Ltd J.V.

Purpose (code) F

Site start 17.12.1990

RCC start 19.11.1992

RCC completion 31.05.1994

Site completion 31.03.1998

Height (m) 57

Length (m) 290

Volume of RCC ($m^3 \times 10^3$) 113

Total volume ($m^3 \times 10^3$) 232

Reservoir capacity ($m^3 \times 10^6$) 6

Upstream slope V

Forming of upstream face (code) (1)

Downstream slope 0.75

Forming of downstream face (code) (1)

Spillway slope 0.75

Forming of spillway face (code) (1)

Depth of layers (mm) 180 - 250

Depth of lifts (mm) 750

Cement content (kg/m^3) 84

Pozzolan content (kg/m^3) 36

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0136

Completed Dam



RCCDAM0136CD

Google Earth



RCCDAM0136GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines