

Dam: Hiyoshi

Country Japan

River Katsura

35°8'50.78"N 135°31'0.84"E

35.147438 135.516907

Owner/Client Water Resources Development Public Corporation

Designer/Engineer Water Resources Development Public Corporation

Contractor Tobishima Construction Ltd., Kohnoike Co Ltd. and Morimoto Co Ltd. J.V.

Purpose (code) F H W

Site start 31.12.1983

RCC start 31.10.1994

RCC completion 31.07.1996

Site completion 31.03.1998

Height (m) 70

Length (m) 438

Volume of RCC ($m^3 \times 10^3$) 440

Total volume ($m^3 \times 10^3$) 670

Reservoir capacity ($m^3 \times 10^6$) 66

Upstream slope V
0.80

Forming of upstream face (code) (1)
(1)

Downstream slope 0.80

Forming of downstream face (code) (1)

Spillway slope 0.80

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm) 750
1000

Cement content (kg/m^3) 84
77

Pozzolan content (kg/m^3) 36
33

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0173

Completed Dam



RCCDAM0173CD

Google Earth



RCCDAM0173GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines