

Dam: Kamuro

Country Japan

River Kaneyama

38°54'39.10"N 140°25'26.35"E

38.910862 140.423981

Owner/Client Yamagata Prefecture

Designer/Engineer Yamagata-ken

Contractor Kajima Co Ltd, Tobishima Construction Co Ltd and Kumagai-gumi Co Ltd (J.V.)

Purpose (code) F W

Site start 22.07.1986

RCC start 04.07.1988

RCC completion 15.10.1990

Site completion 31.08.1993

Height (m) 61

Length (m) 257

Volume of RCC ( $m^3 \times 10^3$ ) 136

Total volume ( $m^3 \times 10^3$ ) 307

Reservoir capacity ( $m^3 \times 10^6$ ) 7

Upstream slope V  
0.60

Forming of upstream face (code) (1)  
(1)

Downstream slope 0.75

Forming of downstream face (code) (1)

Spillway slope 0.75

Forming of spillway face (code) (1)

Depth of layers (mm) 150 -  
200

Depth of lifts (mm) 500

Cement content ( $kg/m^3$ ) 96

Pozzolan content ( $kg/m^3$ ) 24

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0075

## Completed Dam



RCCDAM0075CD

## Google Earth



RCCDAM0075GE

# Guide to Abbreviations

## Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

## Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
  - ' GEVR/GE-RCC
  - \* Stepped face

## Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines