Dam:	Kido	Country	Japan
River	Kido	37°16'17.6"N 140°54'52.18"E	37.271557 140.91449
Owner/Client	Fukushima Prefecture		
Designer/Engineer	Fukushima-ken		
Contractor	Maeda Construction Co. Ltd., Nissan Construction Co. Ltd. and Tanaka Construction Co. Ltd. J.V.		

Purpose (code)	F I N W
Site start	20.10.2000
RCC start	09.06.2003
RCC completion	31.08.2005
Site completion	20.03.2008
Height (m)	94
Length (m)	350
Volume of RCC (m^3x10^3)	291
Total volume (m^3x10^3)	501
Reservoir capacity (m^3x10^6)	19
Upstream slope	V 0.10
Forming of upstream face (code)	(1) (1)
Downstream slope	0.78
Forming of downstream face (code)	(1)
Spillway slope	0.78
Forming of spillway face (code)	(1)
Depth of layers (mm)	250
Depth of lifts (mm)	750 1000
Cement content (kg/m^3)	84
Pozzolan content (kg/m^3)	36
Code for pozzolan	(F)
RCCDAM Unique Serial No.	RCCDAM0341

Completed Dam

RCCDAM0341CD

Google Earth

RCCDAM0341GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines