

Dam: Koudiat Acerdoune

Country: Algeria

River: Wadi Isser

36°29'18.47"N 3°35'29.82"E

36.488464 3.591617

Owner/Client: ANBT (Agence Nationale des Barrages et Transfert)

Designer/Engineer: Coyne & Bellier

Contractor: Razel

Purpose (code): I W

Site start: 23.11.2002

RCC start: 01.05.2006

RCC completion: 30.06.2008

Site completion: 30.09.2008

Height (m): 121

Length (m): 492

Volume of RCC (m³x10³): 1650

Total volume (m³x10³): 1850

Reservoir capacity (m³x10⁶): 800

Upstream slope: 0.65

Forming of upstream face (code): (1) *

Downstream slope: 0.65

Forming of downstream face (code): (1) *

Spillway slope: 0.65

Forming of spillway face (code): (1) *

Depth of layers (mm): 300 to 400

Depth of lifts (mm): 300 to 400

Cement content (kg/m³): 77

Pozzolan content (kg/m³): 87

Code for pozzolan: (F)

RCCDAM Unique Serial No.: RCCDAM0414

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines