

Dam: Origawa

Country Japan

River Ori

35°19'42.57"N 137°18'10.21"E

35.328491 137.302841

Owner/Client Ministry of Land, Infrastructure & Transport

Designer/Engineer Ministry of Construction

Contractor Satoh Kogyo Co Ltd., Maeda Construction Kogyo Co Ltd. and Dainihon Doboku Co Ltd. J.V.

Purpose (code) F N

Site start 25.02.1993

RCC start 13.11.1996

RCC completion 31.07.2000

Site completion 29.03.2004

Height (m) 114

Length (m) 331

Volume of RCC ( $m^3 \times 10^3$ ) 673

Total volume ( $m^3 \times 10^3$ ) 742

Reservoir capacity ( $m^3 \times 10^6$ ) 15

Upstream slope V  
0.60

Forming of upstream face (code) (1)  
(1)

Downstream slope 0.77

Forming of downstream face (code) (1)

Spillway slope 0.77

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm) 750

Cement content ( $kg/m^3$ ) 91

Pozzolan content ( $kg/m^3$ ) 39

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0235

## Completed Dam



RCCDAM0235CD

## Google Earth



RCCDAM0235GE

# Guide to Abbreviations

## Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

## Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
  - ' GEVR/GE-RCC
  - \* Stepped face

## Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines