

Dam: Rialb

Country Spain

River Segre

41°56'24.12"N 1°11'34.89"E

41.940033 1.193025

Owner/Client Confederación Hidrográfica del Ebro

Designer/Engineer Juan Benet

Contractor Cubiertas y Mzov, S.A.

Purpose (code) I W

Site start 01.01.1993

RCC start 01.10.1995

RCC completion 30.12.1998

Site completion 31.01.2000

Height (m) 99

Length (m) 630

Volume of RCC (m<sup>3</sup>x10<sup>3</sup>) 980

Total volume (m<sup>3</sup>x10<sup>3</sup>) 1016

Reservoir capacity (m<sup>3</sup>x10<sup>6</sup>) 402

Upstream slope 0.15  
0.35

Forming of upstream face (code) (1)  
(1)

Downstream slope 0.40  
0.65

Forming of downstream face (code) (1)  
(1)

Spillway slope 0.65

Forming of spillway face (code) (1)

Depth of layers (mm) 330

Depth of lifts (mm) 330

Cement content (kg/m<sup>3</sup>) 70  
65

Pozzolan content (kg/m<sup>3</sup>) 130  
130

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0204

## Under Construction



RCCDAM0204UC

## Completed Dam



RCCDAM0204CD

## Google Earth



RCCDAM0204GE

# Guide to Abbreviations

## Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

## Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
  - ' GEVR/GE-RCC
  - \* Stepped face

## Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines