

Dam: Satsunaigawa

Country Japan

River Satsunai

42°35'17.75"N 142°55'22.17"E

42.588264 142.922821

Owner/Client Hokkaido Development Bureau

Designer/Engineer Hokkaido Development Bureau

Contractor Hazama-gumi Ltd., Chizaki Kogyo Co Ltd. and Mitsui Construction Co Ltd. J.V.

Purpose (code) F H I W

Site start 01.02.1987

RCC start 01.04.1991

RCC completion 31.10.1995

Site completion 31.03.1999

Height (m) 114

Length (m) 300

Volume of RCC ($m^3 \times 10^3$) 536

Total volume ($m^3 \times 10^3$) 770

Reservoir capacity ($m^3 \times 10^6$) 54

Upstream slope 0.40

Forming of upstream face (code) (1)

Downstream slope 0.80

Forming of downstream face (code) (1)

Spillway slope 0.80

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm) 750

Cement content (kg/m^3) 78

Pozzolan content (kg/m^3) 42

Code for pozzolan (S)

RCCDAM Unique Serial No. RCCDAM0158

Completed Dam



RCCDAM0158CD

Google Earth



RCCDAM0158GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines