

Dam: Shiokawa

Country Japan

River Shio

35°51'31.21"N 138°29'52"E

35.858669 138.497772

Owner/Client Yamanashi Prefecture

Designer/Engineer Yamanashi-ken

Contractor Taisei Construction Co Ltd., Toda Construction Co Ltd. and Nagata-gumi Ltd. J.V.

Purpose (code) F I W

Site start 01.05.1993

RCC start 01.08.1993

RCC completion 30.11.1995

Site completion 31.03.1999

Height (m) 79

Length (m) 225

Volume of RCC ($m^3 \times 10^3$) 299

Total volume ($m^3 \times 10^3$) 388

Reservoir capacity ($m^3 \times 10^6$) 12

Upstream slope 0.10
0.70

Forming of upstream face (code) (1)
(1)

Downstream slope 0.76

Forming of downstream face (code) (1)

Spillway slope 0.76

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm) 750

Cement content (kg/m^3) 96

Pozzolan content (kg/m^3) 24

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0161

Completed Dam



RCCDAM0161CD

Google Earth



RCCDAM0161GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines