

Dam: Shiyazi

Country: China

River: Hongdu

28°39'6.22"N 107°58'4.62"E

28.651728 107.967949

Owner/Client: Guizhou Zhongshui Energy Co. Ltd.

Designer/Engineer: Hydrochina Guiyang Engineering Corporation

Contractor: SinoHydro Construction Bureau N^o9 Co. Ltd.

Purpose (code): H

Site start: 01.01.2007

RCC start: 01.04.2008

RCC completion: 24.12.2011

Site completion: 30.12.2011

Height (m): 135

Length (m): Unknown

Volume of RCC (m³x10³): Unknown

Total volume (m³x10³): Unknown

Reservoir capacity (m³x10⁶): 321

Upstream slope: Unknown

Forming of upstream face (code): Unknown

Downstream slope: Unknown

Forming of downstream face (code): Unknown

Spillway slope: Unknown

Forming of spillway face (code): Unknown

Depth of layers (mm): Unknown

Depth of lifts (mm): Unknown

Cement content (kg/m³): Unknown

Pozzolan content (kg/m³): Unknown

Code for pozzolan: Unknown

RCCDAM Unique Serial No.: RCCDAM0508

Under Construction



RCCDAM0508UC

Completed Dam



RCCDAM0508CD

Google Earth



RCCDAM0508GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines