

Dam: Tongjiezi (with Niurixigou saddle dam)

Country China

River Dadu

29°15'22.57"N 103°38'1.35"E

29.256269 103.633705

Owner/Client Guodian Dadu River Basin Hydropower Development Co.

Designer/Engineer Chendu Hydroelectric Power Investigation & Design Institute, MOE & MWR

Contractor 7th Construction Bureau, MOE & MWR

Purpose (code) F H I N

Site start 01.01.1985

RCC start 01.10.1988

RCC completion 30.12.1989

Site completion 31.10.1994

Height (m) 88

Length (m) 1029

Volume of RCC ($m^3 \times 10^3$) 407

Total volume ($m^3 \times 10^3$) 855

Reservoir capacity ($m^3 \times 10^6$) 200

Upstream slope V

Forming of upstream face (code) (1)

Downstream slope 0.75

Forming of downstream face (code) (10)

Spillway slope 0.75

Forming of spillway face (code) (1)

Depth of layers (mm) 300 - 500

Depth of lifts (mm) 300 - 500

Cement content (kg/m^3) 79 82

Pozzolan content (kg/m^3) 79 83

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0058

Completed Dam



RCCDAM0058CD

Google Earth



RCCDAM0058GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines