

Dam: Tsugawa

Country Japan

River Kamo

35°10'4.72"N 134°6'32.91"E

35.167976 134.109146

Owner/Client Okayama Prefecture

Designer/Engineer ?

Contractor Tobishima Construction Co Ltd, Hazama-gumi Construction Co Ltd and Aisawa Construction Co Ltd J.V.

Purpose (code) F H W

Site start 01.10.1989

RCC start 01.10.1991

RCC completion 31.07.1993

Site completion 31.03.1994

Height (m) 76

Length (m) 228

Volume of RCC (m<sup>3</sup>x10<sup>3</sup>) 222

Total volume (m<sup>3</sup>x10<sup>3</sup>) 342

Reservoir capacity (m<sup>3</sup>x10<sup>6</sup>) 6

Upstream slope V  
0.60

Forming of upstream face (code) (1)  
(1)

Downstream slope 0.76

Forming of downstream face (code) (1)

Spillway slope 0.76

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm) 750

Cement content (kg/m<sup>3</sup>) 96

Pozzolan content (kg/m<sup>3</sup>) 24

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0120

## Completed Dam



RCCDAM0120CD

## Google Earth



RCCDAM0120GE

# Guide to Abbreviations

## Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

## Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
  - ' GEVR/GE-RCC
  - \* Stepped face

## Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines