

Dam: Yamba

Country Japan

River Agatsuma

36°33'24.56"N 138°42'49.85"E

36.556824 138.713852

Owner/Client Ministry of Land, Infrastructure, Transport and Tourism

Designer/Engineer Idowr Engineering Co. Ltd. (Nippon Koei)

Contractor Shimizu Corp., IHI Infrastructure Systems Co. and Tekken Corp. JV

Purpose (code) F H I N W

Site start 01.08.2008

RCC start 01.05.2017

RCC completion 31.05.2019

Site completion 30.06.2020

Height (m) 116

Length (m) 291

Volume of RCC ($m^3 \times 10^3$) 575

Total volume ($m^3 \times 10^3$) 911

Reservoir capacity ($m^3 \times 10^6$) 108

Upstream slope 0.15

Forming of upstream face (code) (1)

Downstream slope 0.80

Forming of downstream face (code) (1)

Spillway slope 0.08

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm) 1000

Cement content (kg/m^3) 91

Pozzolan content (kg/m^3) 39

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM0708

Under Construction



RCCDAM0708UC

Google Earth



RCCDAM0708GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines