Dam:	Zintel Canyon	Country	USA
River	Zintel	46°10'29.19"N 119°11'1.47"W	46.174774 -119.183739
Owner/Client	City of Kennewick, Washington		
Designer/Engineer	USACE, Walla Walla District		
Contractor	Delhur Industries, In., Port Angeles, Washington		

Purpose (code)	F
Site start	01.03.1992
RCC start	06.07.1992
RCC completion	15.10.1992
Site completion	09.12.1992
Height (m)	39
Length (m)	158
Volume of RCC (m^3x10^3)	54
Total volume (m^3x10^3)	55
Reservoir capacity (m^3x10^6)	3
Upstream slope	V
Forming of upstream face (code)	(7)
Downstream slope	0.85
Forming of downstream face (code)	(17)
Spillway slope	0.85
Forming of spillway face (code)	(17)
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	74
Pozzolan content (kg/m^3)	0
Code for pozzolan	(-)
RCCDAM Unique Serial No.	RCCDAM0104

Under Construction

RCCDAM0104UC

Completed Dam



RCCDAM0104CD

Google Earth

RCCDAM0104GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines