

Dam: Jupudu

Country: China

River: Lixian (Black)

22°54'10.37"N 100°46'23.44"E

22.902882 100.773178

Owner/Client: Datang International Power Generation Co. Ltd.

Designer/Engineer: Kunming Hydroelectric Investigation, Design and Research Institute, CHECC

Contractor: Gezhouba Construction Bureau & 4th Construction Bureau

Purpose (code): H

Site start: 01.11.2004

RCC start: 01.01.2005

RCC completion: 31.12.2006

Site completion: 31.12.2007

Height (m): 95

Length (m): 320

Volume of RCC ($m^3 \times 10^3$): 480

Total volume ($m^3 \times 10^3$): 800

Reservoir capacity ($m^3 \times 10^6$): 174

Upstream slope: V
0.20

Forming of upstream face (code): (3)

Downstream slope: 0.80

Forming of downstream face (code): (3)

Spillway slope: 0.80

Forming of spillway face (code): (3)

Depth of layers (mm):

Depth of lifts (mm):

Cement content (kg/m^3):

Pozzolan content (kg/m^3):

Code for pozzolan:

RCCDAM Unique Serial No.: RCCDAM0392

Under Construction



RCCDAM0392UC

Completed Dam



RCCDAM0392CD

Google Earth



RCCDAM0392GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines